



TEST REPORT

LAB NO.: (6620)134-0589
FORM NO.: /
DATE IN: May 13, 2020
DATE OUT: May 21, 2020
NO. OF WORKING DAYS: 7
PAGE 1 OF 3

OVERALL RATING

PASS	<u> X </u>
FAIL	<u> </u>
DATA	<u> </u>

Vendor:	WORLDCHAMP (HUIZHOU) PLASTICS PRODUCTS CO.,LTD	Agent:	/
Fabric Supplier/Mill:	/	Factory/Manufacturer:	/
P.O. No.:	/	Style No.:	/
Sample Description:	AAMI LEVEL 2 CPE/LDPE GOWN	Style Description:	/
Color:	BLUE	Country of Origin:	/
Claimed Fabric Weight:	/	Claimed Fabric Count:	/
Yarn Size:	/	Submitted Size:	/
Size Range:	/	FPU No.:	/
GPU No.:	/	End Use:	PERSONAL PROTECTION
SKU:	/		

Product Category	/
Test Requested	PARTIAL TEST
Previous Report No.	/

Submitted Fiber Content	/
Actual Fiber Content	/
Suggested Fiber Content	/
Submitted Care Instruction(s)	/
Client Expected Care Instruction	/
Suggested Care Instruction(s)	/

Bureau Veritas Consumer Products Services
 Division
 (Shanghai)
 No. 168, Guanghua Road, Zhuanqiao Town,
 Minhang,
 Shanghai China, 201108
 Tel: 86-21-24081888, Fax: 86-21-64890042
 Email: bvcpsh.sh.info@cn.bureauveritas.com
 website: <http://www.bureauveritas.cn/cps>
 (China) |
<http://www.bureauveritas.com/cps> (Global)

This report is governed by, and incorporates by reference, CPS Conditions of Service as posted at the date of issuance of this report at <http://www.bureauveritas.com/home/about-us/our-business/cps/about-us/terms-conditions/> and is intended for your exclusive use. Any copying or replication of this report to or for any other person or entity, or use of our name or trademark, is permitted only with our prior written permission. This report sets forth our findings solely with respect to the test samples identified herein. The results set forth in this report are not indicative or representative of the quality or characteristics of the lot from which a test sample was taken or any similar or identical product unless specifically and expressly noted. Our report includes all of the tests requested by you and the results thereof based upon the information that you provided to us. Measurement uncertainty is only provided upon request for accredited tests. You have 60 days from date of issuance of this report to notify us of any material error or omission caused by our negligence or if you require measurement uncertainty; provided, however, that such notice shall be in writing and shall specifically address the issue you wish to raise. A failure to raise such issue within the prescribed time shall constitute your unqualified acceptance of the completeness of this report, the tests conducted and the correctness of the report contents.



**BUREAU
VERITAS**

LAB NO: **(6620)134-0589**

Page 2 of 3

TEST PROPERTY	PASS	FAIL	DATA	COMMENTS
WATER RESISTANCE: HYDROSTATIC PRESSURE TEST	X			
WATER RESISTANCE: IMPACT PENETRATION TEST	X			

Remark:

1. With the client's prior consent, WATER RESISTANCE: IMPACT PENETRATION TEST was subcontracted test item.
2. BVCPS (Shanghai) contact information for this report

Address: No.168, Guanghua Road, Zhuanqiao Town, Minhang, Shanghai, China.

General Information:

Jojo Li	086-021-24081666*9309, email: jojo-wj.li@cn.bureauveritas.com
Noah Zhang	086-021-24081666*9307, email: Xiaoliang.zhang@cn.bureauveritas.com
Seven Sun	086-021-24081666*9327, email: Seven.sun@cn.bureauveritas.com
Du Shuang	086-021-24081675, email: shuang.du@cn.bureauveritas.com
Challenge Qiao	086-021-24081666*9331, email: challenge.qiao@cn.bureauveritas.com
Lizzy Liao	086-021-24081666*9303, email: lizzy.liao@bureauveritas.com
Sherry Shen	086-021-24081666*9310, email: shirley-ll.shen@cn.bureauveritas.com

Technical Questions:

Pat Liu	086-021-24081745, email: Pat.liu@cn.bureauveritas.com
Rio Zhang	86-21-24081666*9305, email: Rio.Zhang@cn.bureauveritas.com

▪ **BUREAU VERITAS**▪

▪ **CONSUMER PRODUCTS SERVICES (SHANGHAI)**▪

▪ ▪

▪ **NONO XIAO**▪

▪ **OPERATION MANAGER**▪



**BUREAU
VERITAS**

LAB NO: **(6620)134-0589**
Page 3 of 3

<u>TEST PROPERTY</u>	<u>TEST RESULTS</u>				<u>REQUIREMENTS</u>
<u>WATER RESISTANCE: HYDROSTATIC PRESSURE TEST</u> (AATCC 127, OPTION 2, HYDROSTATIC HEAD TESTER AT 60 MBAR/MIN, DISTILLED OR DEIONIZED WATER AT 21+/-2 DEGREE CELSIUS)					
BEFORE WASH (CM H ₂ O)	1	2	3	AVE	
FABRIC	>20	>20	>20	>20	MIN. 20CM H ₂ O
SLEEVE	>20	-	-	-	MIN. 20CM H ₂ O
<u>WATER RESISTANCE: IMPACT PENETRATION TEST</u> (AATCC 42-17)					
MAIN BODY	1	2	3	AVE	
INCREASED MASS (GRAM)	0.0	0.0	0.0	0.0	MAX. 1.0GRAM
SEAM	1	2	3	AVE	
INCREASED MASS (GRAM)	0.0	0.0	-	0.0	MAX. 1.0GRAM



END OF REPORT